

Betiocryl 757 TX 60



RESINA ACRILICA

Resina acrílica termoplástica

ACRYLIC RESIN

Thermoplastic acrylic resin

COMPOSICION

Resina Acrílica Copolímero Termoplástica

COMPOSITION

Copolymer thermoplastic acrylic resin

- Composición del solvente

Tolueno	80%
Xileno	20%

- Solvent composition

Toluene	80%
Xylene	20%

SPECIFICATIONS/ ESPECIFICACIONES				
Non volatiles / Solidos	60± 1	%	D-116/4	ASTM D1644
Viscosity / Viscosidad	Z3- Z5	Gardner	D-055	ASTM D1545
Colour / Color	max 2	Hellige	D-019	ASTM D1545-NI1109
Acid Value/Índice Acidez	max 14	mgKOH/g	D-149	-----
Appearance / Apariencia	Clear/ Transparent Clara/Transparente	Visual	D-020	-----
Density / Densidad	0,98 ± 0.02	Kg / dm ³	D-022	DIN 53217
Flash Point/ Punto inflamacion	9	°C	D-547	DIN 53213

(*) Methods of determination (available on request)/ Metodos de determinación (disponibles a pedido)

SOLUBILIDAD

Solventes aromáticos	completa
Solventes alifáticos	mala
Esteres y cetonas	completa

SOLUBILITY

Aromatic solvents	complete
Aliphatic solvents	not dilutable
Esters and ketones	complete

COMPATIBILIDAD

Plastificantes	buena
Nitrocelulosa 1/2 seg.	limitada

COMPATIBILITY

Plasticizers	good
Nitrocelullose 1/2 seg.	limited

PROPIEDADES PRINCIPALES

Excelente vehículo para pinturas de demarcación vial, muy rápida evaporación de solvente y resistencia a la abrasión.

MAIN PROPERTIES

Excellent binder in the formulation of road marking paints, due to its very good solvent release and abrasion resistance

APLICACIONES

Pinturas para demarcación vial, aplicables en frío y reflectivas por esferas de vidrio.
Pinturas para concreto, combinada con plastificantes si se requiere gran flexibilidad

APPLICATIONS

Traffic paints for cold application and reflective by glass beads.
Concrete paints combined with plasticizers when extreme flexibility is required.

FORMAS DE USO

BCryl 757 sola o con 20-30% Parafina clorada

USES

BCryl 757 alone or combined with 20-30% of Chlorinated paraffin

FORMAS DE ENTREGA

Al 60% en Tolueno/Xileno en tambores de hierro con 180 kg netos.

SUPPLIED FORMS

60% in Toluene/Xylene in drums containing 180 kg net.

Nota: los datos arriba consignados se han obtenido de ensayos realizados en nuestro laboratorio. Los mismos son altamente confiables, pero declinamos toda responsabilidad respecto al uso que se haga de ellos.

Note: The above mentioned indications are based on carefully made tests in our laboratory. However, no liability can be assumed in the event of any inaccuracy or incompleteness being found in the value listed above.